



FORTA-FI™

FACT-DATA®

MANUFACTURER

FORTA® CORPORATION, 100 Forta Drive, Grove City, PA, 16127-6399 U.S.A.

GENERAL DESCRIPTION

FORTA-FI™ is a family of three synthetic fiber blends formulated to reinforce Hot Mix Asphalt (HMA), Warm Mix Asphalt (WMA), and hot/cold Asphalt Patch (PAT). By controlling thermal, reflective and fatigue cracking, as well as rutting, FORTA-FI provides the benefit of immediate cost savings through reduced asphalt thickness or extended asphalt life, or both. The proprietary blends contain aramid and polyolefin fibers and other materials, known for their strength, durability, and binding properties.

APPLICATIONS

FORTA-FI is designed to three-dimensionally reinforce all asphalt mixtures. By controlling thermal, reflective and fatigue cracking, as well as rutting, FORTA-FI is a cost-effective way to improve the durability and longevity of a wide variety of HMA, WMA and PAT asphalt applications. FORTA-FI may be used in overlays, surface or base and courses of asphalt pavements. Specific application areas include streets, roadways, commercial and industrial parking lots, and residential driveways.

INSTALLATION

FORTA-FI mixes well in both batch plants and drum plants at all production speeds. It is added to the mixture, while still in the bag, at any point in the mixing process after the fines collection and before the addition of liquid asphalt. While the fibers disperse uniformly and completely in seconds, it's best to leave as much mixing time as is practical within your typical mixing process.

PHYSICAL PROPERTIES

Materials.....	Polyolefin/Aramid	Length.....	3/4" (19mm)
Form.....	Twisted Fibrillated & Monofilament Fibers	Color.....	Yellow, Black, Tan
Specific Gravity.....	0.91/1.44	Acid/Alkali Resistance...	Inert
Tensile Strength....	70,000 p.s.i./400,000 p.s.i.	Melt Temperature.....	302°F / 800°F (150°C / 427°C)

AVAILABILITY

FORTA-FI can be purchased exclusively from **HES**, the sole authorized FORTA products distributor. Orders ship within 24 hours of cleared payment by commercial carrier or air freight.

PACKAGING

	<u>For US Short Ton</u>	<u>For Metric Ton</u>
Bags.....	1.0 Pound, (0.45Kg)	0.5 Kilograms
Cartons.....	40 Bags	35 Bags
Pallets.....	16 Cartons/640 Bags	16 Cartons/560 Bags

WARRANTY

FORTA® products are warranted to be free of defects in material and meet all quality control standards set by the manufacturer. FORTA Corporation specifically disclaims all other warranties, express or implied. The exclusive remedy for defective product shall be to replace the product or refund the purchase price. No agent or employee of this company is authorized to vary the terms of this warranty notice. FORTA Corporation has no control over the design, production, placement, or testing of the concrete products in which FORTA products are incorporated, and therefore FORTA Corporation disclaims liability for the end product.

FORTA Corporation's technical recommendations regarding synthetic fiber characteristics are based on years of engineering research and scores of projects. FORTA has developed a simple "4-C's" formula to help the specifier choose the right fiber for any project application. By making a decision with each of the FORTA "4-C's" categories — Configuration, Chemistry, Contents, and Correct Length — specifiers are assured of obtaining the desired fiber performance level for a given project. The following 4-C's Formula Specification has been prepared to accommodate the stated reinforcement objective for this FORTA product grade.

REINFORCEMENT OBJECTIVE: To three-dimensionally reinforce Hot Mix Asphalt pavements by controlling reflective cracking, shoving, rutting, and other stability-related problems.

DIVISION – ASPHALT

SECTION – ASPHALT REINFORCEMENT/MODIFIERS

SUB-SECTION – SYNTHETIC FIBROUS REINFORCEMENT

Synthetic fibrous reinforcement shall be used in the areas denoted in plans, and shall comply with the following fiber characteristics:

1. **Configuration** – Fiber shall be a blend of twisted-bundle network fibers and high-strength monofilament fibers.
2. **Chemistry** – Fiber shall be made of aramid (monofilament) and polyolefin (twisted-bundle & monofilament) fibers and other materials, known for their strength, durability, and binding properties.
3. **Contents** – Fiber shall be used at a minimum dosage rate of 1.0 pounds per ton (0.5 Kg. per metric ton) of asphalt.
4. **Correct Length** – Fiber length shall be 3/4" (19mm).

APPROVED PRODUCT: FORTA-FI as manufactured by FORTA Corporation, Grove City, PA, U.S.A.



Heavy Equipment Solutions Inc.

75 boul. de Mortagne Suite 116
Boucherville, Quebec, J4B 6Y4, Canada
info@jas-hes.com • www.jas-hes.com
Tel: +1.450.641.5445 • Fax: +1.450.641.7595